



**Summary of Substantive Changes  
between the 2015 and the 2020 editions of  
ASTM D2241 “Poly (Vinyl Chloride) (PVC) Pressure-Rated Pipe (SDR Series)”**

**Presented to the IAPMO Standards Review Committee on November 9, 2020**

**General:** The changes to this standard should not have an impact on currently listed products. The substantive change is:

- Increased relative humidity tolerance for test specimen conditioning and test conditions from 5% to 10% (see Sections 8.1, and 8.2)

Section 8, Test Methods: The relative humidity tolerances have been revised as follows:

**8.1 Conditioning**—*Unless otherwise specified in the applicable test method, condition the test specimens at  $73.4 \pm 3.6$  °F ( $23 \pm 2$  °C) and  $50 \pm 5\%$  10 % relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice D618 for those tests where conditioning is required.*

**8.2 Test Conditions**—*Conduct the tests in the standard laboratory atmosphere of  $73.4 \pm 3.6$  °F ( $23 \pm 2$  °C) and  $50 \pm 5\%$  10 % relative humidity, unless otherwise specified in the test methods or in this specification.*