



**Summary of Substantive Changes
between the 2015 and the 2020 editions of
ASTM D2467 “Poly (Vinyl Chloride) (PVC) Plastic Pipe Fittings, Schedule 80”**

Presented to the IAPMO Standards Review Committee on October 18, 2021

General: The change to this standard should not have an impact on currently listed products. The substantive change is:

- Expanding tolerance of test conditions regarding relative humidity from 5% to 10% (see Section 8.2)

Section 8, Test Methods: Expanded tolerance of test conditions regarding relative humidity from 5% to 10% as follows:

8. Test Methods

8.1 Conditioning—*Condition the test specimens at $73.4 \pm 3.6^{\circ}\text{F}$ ($23 \pm 2^{\circ}\text{C}$) and $50 \pm 10\%$ relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice D618, for those tests where conditioning is required.*

8.2 Test Conditions—*Conduct tests in the Standard Laboratory Atmosphere of $73.4 \pm 3.6^{\circ}\text{F}$ ($23 \pm 2^{\circ}\text{C}$) and 50 ± 5 10% relative humidity, unless otherwise specified in the test methods or in this specification.*