



**Summary of Substantive Changes
between the 2015 and the 2016 editions of
ASTM F667, “3 through 24 in. Corrugated Polyethylene Pipe and Fittings”**

Presented to the IAPMO Standards Review Committee on August 8, 2016

General: The changes to this standard should not have an impact on currently listed products. The substantive changes are:

- Addition of a footnote allowing substitution of material class pigments (see Section 5.1).
- Allowance of perforations inlet area specification by the user (see Section 7.3.2).

Section 5.1, *Basic Materials*—Compounds used in the manufacture of corrugated PE drainage pipe and fittings shall have a minimum cell classification of 323410C or 333410C as defined and described in Specification D3350. Compounds that have a higher cell classification in one or more properties are acceptable, provided the product requirements are met.

NOTE 1—Class B pigments may be substituted for Class C provided that ultraviolet protection is acceptable to the publisher as satisfactory for the intended use.

Section 7.3 *Perforations:*

Section 7.3.1 *Drainage Pipe*—When perforations are necessary, they shall be cleanly cut and uniformly spaced along the length and circumference of the pipe in a size, shape, and pattern suited to the needs of the user.

Section 7.3.2, The inlet area of the perforations shall be a minimum of 1 in.2/ft [21 cm2/m] of pipe, *unless otherwise specified by the user.*